



Mintepox® MMA SL 362 Technical Data Sheet

Methacrylate Main Coat Resin

Specification:

- Viscosity, 23 °C 180 - 200 mPa·s (MH1007 / ISO 3219)
- Appearance Opaque liquid

Remarks:

- Middle viscous, elasticised methacrylate resin used for flooring.
- Mintepox® MMA SL 362 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- Mintepox® MMA SL 362 is amine pre-activated.

Applications:

- Reactive 2-pack methacrylate resin, hardened with dibenzoyl peroxide.
- For proper curing at 20 °C add 2% hardener in respect to resin.
For different temperatures, adjust hardener amount.
- Suitable for self levelling applications. Application trowel.
- Typical consumption: 1,70 kg/m² (for 3 mm thickness)
- Recommended thickness 2,00 mm – 4,00 mm

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.

EPOZEM

e