



Mintepox® MMA Topping 972 Technical Data Sheet

Methacrylate Topping

Specification:

- Viscosity, 23 °C 180 - 200 mPa·s (MH1007 / ISO 3219)
- Appearance Bluish opaque liquid

Remarks:

- Middle viscous, hard methacrylate resin used for flooring.
- Mintepox® MMA Topping 972 contains paraffin which tends to float when stored for a long period of time at lower temperatures. Therefore, the binder must be homogenized before use by stirring.
- Mintepox® MMA Topping 972 is amine pre-activated.

Applications:

- Reactive 2-pack methacrylate resin, hardened with dibenzoyl peroxide.
- For proper curing at 20 °C add 1,5 % hardener in respect to resin.
For different temperatures, adjust hardener amount.
- Suitable for topping applications. Application with rollers and squeegee.
- Typical consumption: 0,60 kg/m²
- Recommended thickness 0,20 mm – 0,80 mm

Storage:

The resin should be stored indoors in its original, unopened and undamaged container in a dry place at storage temperatures between 5 °C and 25 °C, for up to 6 months. Exposure to direct sunlight should be avoided.